



HYCHEM SF20

Heavy duty epoxy coating with good colour stability

Hychem SF20 is a solventless, chemical resistant, two components epoxy coating with high solvent resistance and good colour stability.

USE

HYCHEM SF 20 is the preferred product of choice for floor & wall coatings in the architectural and pharmaceutical industries where aesthetic qualities are of high importance. It is not recommended for applications where exposure to acetic and lactic acid is commonplace.

FEATURES AND BENEFITS

- Non yellowing & suitable for pastel finishes
- Chemical resistant to petroleum oils, solvents, acids & alkalies, hot fats
- Durable – 100% solids provides a 500 micron DFT (two coat application)
- Wear resistant – hard wearing even in harsh and punishing environment.
- Slip resistance – meets AS/NZ 4568 R10, will meet R11 to R13 with quartz aggregates
- Solventless – non-flammable
- Odourless – can be used in retail situations without disturbing neighbouring businesses
- Aesthetic flexibility – available in a variety of colours
- High gloss finish – aesthetically pleasing, easy to maintain
- Wide colour range – available in many colours (colour matching on request)

PHYSICAL PROPERTIES @ 25°C

| | |
|--------------------------------------|---|
| Solids content | 100 % |
| Pot life | 25 mins |
| Mix ratio by volume (Resin:Hardener) | 2:1 |
| Initial cure | 9 hours |
| Re-coat time | 24 hours |
| Cure time | 24 hours – light traffic 72 hours – full traffic |
| Film thickness per coat | 200–300 microns |
| Slip resistance ANZ4586:2004 | R10—R13 dependent on anti-slip |
| Colour stability | Excellent indoors |

TYPICAL APPLICATIONS

- Bulk retail outlets & warehouses
- Component manufacturers
- Commercial kitchens & bars
- Exhibition halls
- Gaols & police stations
- Hospitals & nursing homes
- Motor workshops & aircraft hangars
- Pharmaceutical plants
- Schools & colleges

CHEMICAL RESISTANCE

The chemical resistance of a material is generally determined by immersing the material in the designated chemical and then seeing whether the material gains or loses wt over time. The greater the change in wt, the poorer is the resistance to that chemical. The table below shows the relative absorption after 7 days immersion. A value of 100 represents an increase in wt of 3%.

| | | | | | |
|---------------------|-----------|------------------|-----|-------------------------|-----|
| 20% Phosphoric acid | 120 | 10% Acetic | 250 | 50% Sodium hydroxide | 0 |
| 20 % Sulphuric acid | 0 | 10% Lactic acid | 150 | 35% Hydrogen peroxide | 30 |
| 70% Sulphuric acid | 20 | Xylene | 5 | 10% Sodium hypochlorite | 25 |
| 98% Sulphuric acid | destroyed | Ethanol | 180 | Skydrol | 5 |
| Toluene | 65 | Butyl Cellosolve | 85 | MEK | 700 |
| Trichlorethylene | 15 | Water | 15 | Conc Hydrochloric acid | 40 |

APPLICATION GUIDELINES

Surface Preparation

- Concrete substrate shall be firm, clean and dry with a compressive strength of 25 MPa and surface tensile strength of 1.5 MPa minimum
- New concrete must be allowed to cure for a minimum of 28 days
- Repair imperfections (holes and cracks) with an epoxy patching compound such as Hychem GP where necessary
- Remove surface laitance, contaminants, coating, curing compound and all weak and loose materials
- Prepare concrete surface by Diamond Grinding or light Shot Blasting to provide the appropriate surface profile for optimum mechanical keying

Priming

- Priming is generally not required
- Where necessary, apply Hychem E 100 by roller at a rate of 5 to 6 sqm/litre

MIXING

Mix only enough quantity that can be applied within the work life which is temperature dependent

- For Hychem SF20 Neutral, add colour pigment into the Component A (Resin) and mix until homogeneous (1 minute) using a helical mixer at a speed of 500 rpm
- Mix Hychem SF20 liquid components (Resin & Hardener) together using a helical mixer at a speed of 500 rpm until the mix becomes homogeneous (1.5 to 2 minutes)
- Move the mixer around from side to side and top to bottom and scrap the sides of the mixing vessel to ensure thorough mixing

APPLICATION

Smooth Finish

- Apply **Hychem E 100 Primer** (where necessary) using a squeegee or short nap roller at a coverage rate of 6 to 8 sqm per litre depending on the coarseness of the sub-floor surface. Allow to cure for a minimum of 12 hours or over-night but less than 24 hours.
- Apply first coat of **Hychem SF20** using a squeegee or short nap roller at a coverage rate of 3 to 4 sqm. Allow to cure as above.
- Apply second coat of **Hychem SF20** at a coverage rate of approximately 4 to 6 sqm per litre. Allow to cure as above.

Non-Slip Finish

- Apply as above. Broadcast grit aggregate (size to suit anti-slip requirement) into the First Coat while it is still wet and allow to cure overnight.
- Sweep off loose quartz aggregate.
- Apply second coat of Hychem SF20 to seal the surface.

Slip Resistance is dependent on the size (grading) of aggregates used:

- 80 mesh Alumina – R 11
- 36 mesh Alumina – R 12
- 24 mesh Alumina – R 13

CLEAN UP

Xylene can be used for cleaning tools and equipment before the mixed compound begins to harden.

COVERAGE

| | |
|-----------------------------|---|
| Hychem E 100 Primer | 6 to 8 sqm/litre (depending on the porosity and texture of the surface) |
| First coat | 5 to 6 sqm/litre (depending on the porosity and texture of the surface) |
| Second coat | 6 to 8 sqm/litre |
| Over self-levelling topping | 6 to 8 sqm/litre |
| Over trowelled on topping | 4 to 6 sqm/litre |

SAFETY PRECAUTIONS

- Wear gloves, eye protection and overalls during mixing and application.
- Ensure there is adequate ventilation and avoid breathing the vapour

PACKAGING

| COLOUR | KIT SIZE | NO. OF COLOUR PACK REQUIRED |
|---------|------------|-----------------------------|
| Neutral | 8.25 Litre | 1 X 0.75 Litre |
| Colour | 9 Litre | None |

SHELF LIFE

12 months from date of manufacture, stored under shelter at 25°C in original un-opened container.

WARNING – ENVIRONMENTAL CONDITIONS

Epoxy products are sensitive to the prevailing temperature and humidity at the time of application.

- High temperatures will shorten the pot life and application may become difficult due to insufficient time being available to lay the product.
- Low temperatures and high humidity will result in the epoxy reacting with moisture to produce a white powdery finish. The tendency to surface whiten depends on the hardener being used and is a common occurrence at temperatures below 16 degC. The use of epoxy coatings below 10 degC is not recommended as this blooming effect can generally not be prevented at temperatures below this point.
- The white surface finish does not affect the structural strength and on site performance but can affect the adhesion of further surface coats.
- Chemical spillage of acids and sanitizing agents may attack the pigments used in the coating and result in discolouration.
- Differing epoxy products have differing resistance to chemicals, always ensure that the correct product is chosen for the service environment to be encountered.

NOTE: Customer responsibility

The technical information and application advice here given is based on the best information available at the time of print. As the information herein is of a general nature, no assumption can be made as to the products suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation.

Field support, where provided, does not constitute supervisory responsibility. Suggestions made by HYCHEM either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not HYCHEM are responsible for carrying out procedures appropriate to a specific application.